


s a r o m ™
c o m b i n a t i o n s u n e x p e c t e d



TEXTURE LOUNGE
LISBON



LISBON - 901



LISBON - 907



LISBON - 905



LISBON - 904



LISBON - 908



LISBON - 903




LISBON - 909



LISBON - 906



LISBON - 910



LISBON - 911

TEXTURE LOUNGE
LISBON



LISBON - 902



LISBON - 915



LISBON - 916




LISBON - 912



LISBON - 914



LISBON - 913



LISBON - 909

TEXTURE LOUNGE

LISBON

Design	Width (In Cms)	Weight	Composition	Tear Strength	Abrasion Resistance	Colour Fastness to Light	Pilling Resistance	Parten Repeat (If any)
LISBON	145 CMS	290 - 300 GSM	100% Polyster	ISO 13934-2-1999; Instron CRE-1" Grab	More 40000 Cycles	4 - 5	4-5 after 2000 cycles	N/A

1. We do not accept responsibility for any damage resulting from inappropriate use, chemical cleaning or additional impregnation.
2. Test results were gathered from various samples and therefore represent average indicative values.
3. Discolouration caused by clothing fabrics such as jenas does not represent a material defect. Minor colour deviations and discolouring in context of permissible industrial tolerance standards do not constitute reasons for claims .

Washing Instructions



Color may vary from batch to batch

Complimentary Sample File Not For Sale

Product Color May Slightly Vary From Original Due To Photographic Lighting Sources Or Your Screen Settings.



s a r o m ™
c o m b i n a t i o n s u n e x p e c t e d

www.sarom.info